

Pre-Design Table for Concrete Slabs on Ground

BarChip MQ58 - Load Location: Internal












Subgrade Condition		k [N/mm ³]	0.03			0.065			0.10				
		CBR [%]	5			20			35				
		E _{v2} [MPa]	40			80			120				
Load Combinations - Internal Position		BarChip MQ58 Fibre Dosage [kg/m ³]	2.5	3.5	5.0	2.5	3.5	5.0	2.5	3.5	5.0		
			Minimum Slab Thickness [mm]										
Light Distributed Loads		LL: 16 kN/m		100	100	100	100	100	100	100	100	100	100
UDL: 30 kN/m ²													
Medium Distributed Loads		LL: 30 kN/m		120	120	120	100	100	100	100	100	100	100
UDL: 50 kN/m ²													
Very Light Loads Single Rack n x 5 kN		 Pickup Truck 14 kN Axle Load		100	100	100	100	100	100	100	100	100	100
Light Loads Single Rack n x 20 kN		 Forklift FL 1 26 kN		100	100	100	100	100	100	100	100	100	100
Medium Loads Single Rack n x 40 kN		 Forklift FL 2 40 kN		125	120	110	115	110	100	100	100	100	100
Heavy Loads Single Rack n x 60 kN		 Forklift FL 3 63 kN		170	160	150	155	145	135	145	135	125	125
Medium Loads Double Rack n x 40 kN		 Forklift FL 2 40 kN		140	130	120	125	120	110	120	110	105	105
Heavy Loads Double Rack n x 60 kN		 Forklift FL 3 63 kN		170	160	155	155	155	150	155	150	140	140
Very Heavy Loads Double Rack n x 80 kN		 Forklift FL 4 90 kN		205	195	185	190	180	165	170	170	170	170
Heavy Vehicle Loads Truck	 15 tonne	 Forklift FL 3 63 kN		115	110	105	115	110	105	110	110	105	105
75 kN Axle Load (single wheels)													
Very Heavy Vehicle Loads Truck	 36 tonne	 Forklift FL 5 140 kN		180	170	165	170	160	160	160	160	160	160
120 kN Axle Load (twin wheels)													

Table 1: Estimated Values for Subgrade Coefficient *k*

Subgrade	<i>k</i> [N/mm ³]
Well compacted sand	0.05 - 0.10
Very well compacted sand	0.10 - 0.15
Loam or clay (moist)	0.03 - 0.06
Loam or clay (dry)	0.08 - 0.10
Clay with sand	0.08 - 0.10
Crushed stone with sand	0.10 - 0.15
Coarse crushed stone	0.20 - 0.25
Well compacted crushed stone	0.20 - 0.30

Legend

UDL: Uniformly distributed load

LL: Line load

Rack: Single rack foot load

Single rack: Aisle on both sides of rack

Double rack: Back-to-back racking

Forklift: Main axle loads, single wheels

Truck: Main axle loads, single or twin wheels

FL X: Forklift type X according to Eurocode 1 with given max. axle load (EC1, Table 6.6)

Table 2: Definitions and Assumptions for the Design Calculations

Concrete class:	C30/37	Contact area and dimensions:	
Exposure classes:	XC2, XC3, XD3, XM2	Rack dimensions:	2700 x 1100 [mm]
Joint spacing:	max. 6 x 6 [m]	Rack foot plates:	120 x 120 [mm]
Partial load safety factors:		Distance of load superimpositions:	
- for racking:	1.20	Rack feet back-to-back:	300 mm
- for vehicles:	1.60	Rack foot - forklift wheel:	300 mm
- for UDL/LL	1.50	Truck wheel - forklift wheel:	300 mm

Disclaimer and Instructions for Use

This design table is intended to estimate the required thickness of concrete industrial floors and pavements reinforced with BarChip MQ58 macro synthetic fibre by BarChip Inc. The fibre dose rate and the thickness of the fibre reinforced concrete slab on grade is herein calculated for the given ground condition and typical load combinations in internal position (i.e. centre of slab).

The structural design calculations in this table have been carried out in accordance with the UK Concrete Society's Technical Report 34: Concrete Industrial Ground Floors – A guide to design and construction (TR34 4th edition). All stated load values have been increased by the referring partial load safety factor as per Table 2, where further assumptions and definitions for the calculations can be found.

The concrete slab is considered inside a building, i.e. closed and covered, during construction and use. If the intended use of the slab is in external conditions (open to the environment, in construction and/or during

its use) then additional concrete thickness or fibre dose rate will be required to account for environmental impact and intrinsic effects.

TR 34 recommends a minimum slab thickness of 150 mm. Where thicknesses in this table fall below the minimum recommended thickness, these are provided solely for information and it is at the discretion of the user to opt for a thickness that is lower than the recommended minimum by TR34. In general, the slab thickness shall never fall below 100 mm for robustness and reduced curling effects.

A detailed structural design must always be carried out prior to execution of the slab. We appreciate your request for support and can provide you with a full structural design optimised for economy.

BarChip accepts no responsibility for slabs that are constructed based on these tables without prior consultation with BarChip to develop a detailed project specific structural design.

BarChip Inc.

info@barchip.com

Australia: +61 1300 131 158

N. America: +1 704 843 8401

EMEA: +353 (0) 1 469 3197

Asia: +65 6835 7716

S. America: +56 2 2703 1563

Brazil: +55 19 3722 2199



Distributors are located in other regions. For contact details visit www.barchip.com.

Disclaimer: This information has been provided as a guide to performance only, for specific and supervised conditions. The user is advised to undertake their own evaluation and use the services of professionals to determine the product suitability for any particular project or application prior to commercial use. ISO 9001:2015. © BarChip Inc. 2020. PDTBCM58Internal_2020_1.

www.barchip.com